

ANUKAMPA POLYMERS & TECHNOLOGIES PVT. LTD.

PVC COLOUR MASTER BATCHES

Sr. No.	Colour	PROPERTIES				Volatile Loss at 130C for 3 Hrs.	Recommended Loading
		Specific Gravity ± 0.03	Hardness Shore A ± 3	Tensile Strength	Elongation at Break		
		No.	No.	N / mm ²	%		
1	M.B.WHITE	1.45	78	15.0	300	0.4	4%
2	M.B.RED	1.33	80	15.5	300	0.5	4%
3	M.B. BLUE	1.32	78	15.1	300	0.5	4%
4	M.B.GREY	1.39	77	14.5	300	0.6	4%
5	M.B.BROWN	1.32	78	14.2	300	0.6	4%
6	M.B.BLACK	1.33	75	12.8	300	0.7	4%
7	M.B.GREEN	1.35	77	14.5	300	0.5	4%
8	M.B.YELLOW	1.34	75	14.0	300	0.5	4%

NOTE: This is only an indicative list.

1. The above values are based on processing and testing under standard laboratory test conditions. The results may vary based on the actual processing parameters and test conditions.
2. It is recommended to dry the material before use.
3. The information given herein is true to the best of our knowledge. However, we disclaim any liability in connection with above data and recommendations as the conditions of use are beyond our control.
4. Standard packing is in 25 kgs HDPE bags with inner polythene liner.
5. PVC color Master Batches in other special colours like Orange, Violet, Golden Yellow, etc. can also be supplied against confirmed orders.